ACCS
AUSTRALIAN CARPET CLASSIFICATION SCHEME

Environmental Certification Scheme

Carpet Name:	*ROYAL CHARM*
Licensee:	*GODFREY HIRST*
Licence Number:	*1012*
Label Number:	*14030*
Certification Approved:	*28/05/2014*
Level:	*4*
ACCS Contract Grading:	*CMD 2**
ACCS Residential Grading:	*REHD2 6**
Suitable for Stairs:	*Yes*
Date Printed:	*3/09/2021*

Allan Firth

Allan Firth
Secretary ACCS

CARPET
IT JUST FEELS BETTER

AUSTRALIAN CARPET MARK

Administered by the Carpet Institute of Australia Limited ABN 11 006 829 303
PO Box 7172, St Kilda Road, Melbourne Victoria 8004 Tel: (03) 9804 5559 • Fax: (03) 9804 5560
Email: info@carpetoz.com.au • www.carpetinstitute.com.au

This certificate remains the property of the Carpet Institute of Australia Limited.

Carpet Details: **Company: GODFREY HIRST** **Label No: 14030**

Licence No: 1012 **Office No: 5851**

Names:

ROYAL CHARM

Details:

Awarded Res Grade:	REHD2	6*
Awarded Con Grade:	CMD	2*
Registered On:		24/02/2014
Active:		Yes
Date In-Active:		
Manufacture Method:		Tufted
Twist Set:		Superba
Dyeing Method:		Piece Dyed
#Colours/Designs:		0
Backing Type:		Sec Fabric
Felted:		N/A
Spinning System:		BCF
Insect Resist Agent:		N/A
Filament:		/
Master Product:		

Hexapod Scores:

	Texture		Colour		Thickness	
		WA		WA	(mm)	(%)
1500:	4.5	4.5	4.5	4.5	0.3	2.1
8000:	3.5	3.5	4.0	3.5	1.6	11.0

ACCS Test:

	Con	Res	Max
SPM/PH Ratio:	16	16	16
Volume Density:	14.6	14.6	20
Tuft Density:	9	9	9
Dyn Load:	4	4	5
Stat Load:	5	5	5
Soiling Prop:	11	11	16
Abrasion Res:	10	10	10
Sub Total:	69.6	69.6	81
Panel Assess:	14	14	19
Total:	83.6	83.6	100

Calc Residential Grade: REHD2 6*

Calc Contract Grade: CHD 3*

Test Results:

Pile Mass g/m² (oz/yd²):	2380	(70.2)
SPM g/m² (oz/yd²):	2078	(61.3)
Stated Pile Height (mm):		15.0
Minimum Pile Height (mm):		0.0
Maximum Pile Height (mm):		0.0
Dynamic Loading Loss (%):		22.8
Static Loading Loss (%):		9.0
Tex (g/1000m):		320
Measured Pile Thickness (mm):		14.5
Machine Gauge (Tufts/dm):		39.4
Meas Tufts Perp to Selvedge:		39.9
Meas Tufts Para to Selvedge:		50.6
Treated For Soiling Resistance:		No
Soil Resist Inhibitor:		No
Stain Resist Inhibitor:		No

Quality Assurance Test:

Cut Pile (%):	100
Loop Pile (%):	0
Panel Assessment Contract:	14
Panel Assessment Residential:	14

Suitable For Stairs: Yes

Tile: No SheetGoods: No

Fibre Signature: PTT:100

Calculations

Pile Height(mm):	16.3
Tuft Density(per dm²):	2018.9
GSPM(g/m²):	505.0
GSPM (abrasive) (g/m²):	275.0
Soiling Propensity:	11.0 +0.0

OAF Values

OAF: 4.2

Calc Density (+-5%):0.14 0.143 0.15

Base Fibre: TRIEXTA

Benchmarks:

RHD1	0	RHD2	3.5
REHD1	3.5	REHD2	3.5

Environmental Classification:

ECS: Yes

Level: 4

	Calc	B/M	P/F
Acoustic:	14.5	4	PASS
Thermal:	101.2	30	PASS
VOC:			
TVOC	61		

Notes:

24/2/14 Submitted by J Cullen. 26/2/14 Panel awarded REHD2(S) 6* and CMD(S) 2*.
6/5/14 Certified to Interim ECS Level 4. 28/5/14 Panel awarded ECS Level 4.